

**БИОАКТИВ ШИША БГ-1Д**  
**Зиядуллаева Нигора Сагдуллаевна**  
**Нуруллаева Максуда Уктамбаевна.**  
**Тошкент давлат стоматология институти**  
**[maqsudanurullayeva@gmail.ru](mailto:maqsudanurullayeva@gmail.ru)**

Биоактив шиша тиббиёт амалиётида 1984-йилдан бери қўлланилиб келинмоқда. Юз-жағ ва пластик жарроҳликда, сяк нуқсонларини ўринни босадиган материал сифатида ўзини яхши исботлади, шунингдек жағ сягининг алвеоляр ўсиғини катталаштириш жараёни учун хам ишлатила бошланди.

Био-шиша остеоластикада муҳим аҳамиятга эга бўлган қўпгина сифатларга эга, масалан, гемостатик таъсир, фиброз қапсуласиз сукка тушиши ва бошқалар. Бироқ, бу камчиликлардан холи емас: натрий оксидининг юқори миқдори (24,5%) туфайли тана суюқликлари таъсири остида унинг тез биодеградацияси содир бўлади. Шу муносабат билан замонавий тиббий материалшунослик нафақат вақтинчалик механик хусусиятга ега бўлган, балки сяк тўқималарининг тикланишига ҳисса қўшадиган, остеобластик-остеокластик фаоллик ва қайта қуриш даврларини оптималлаштиришга ҳисса қўшадиган янги материалларни излашни давом еттирмокда, шу жумладан резорбсия босқичлари (остеокласт фаоллиги), реверсия ва тиклаш янги сяк тўқималарининг (остеобласт фаолияти) устида ишлар олиб борилмокда.

Замонавий шиша-кристалли материал камчиликлари сяк нуқсонини имплантациядан кейин сяк тўқимасини этарли даражада тикламаслиги. Магний оксида ( $MgO$ ) ва натрий оксида ( $Na_2O$ ) ни материал таркибига киритиш орқали унинг хусусиятларини яхшилашга эришилди, чунки  $Mg^{2+}$  ва  $Na^+$  катионлари шиша ҳужайралараро суюқликка ювиш жараёнида фаол иштирок этади, бу еса калций фосфатларининг чўкишини тезлаштиради. Бироқ, бироз яхшиланган остеорепаратив хусусиятларга эга бўлган бу биологик фаол шиша имплант билан чегарадош сяк тўқималарига токсик бўлиб, бу остеорепарация жараёнларини секинлашишига олиб келади.

Олимлар биологик фаол шишанинг янги таркибини ишлаб чиқиши орқали ушбу камчиликни бартараф этишга муваффақ бўлишиди:

Мод да	Si $O_2$	M $gO$	Ca O	P <sub>2</sub> $O_5$	C $aF_2$	N $a_2O$
Mac .%	46 ,06	8, 83	,66	28 22	6, 70	5, 53

Ушбу материал ВГ-1D деб номланган бўлиб унинг ўзига хос физик-биологик хусусиятлари қуйидагича.

B<sub>2</sub>O<sub>3</sub> ионларнинг шишадан хужайраларо суюқликка тарқалишини секинлаштириши ва шу билан биоаппратит ҳосил бўлишини камайтириши ёки ҳатто ингибир қилиши исботланган. Ушбу маълумотлар экспериментал Ҳенч нинг тадқиқотлар тасдиқланди .У бор катиони шишанинг кремний-кислород тўрига жойлаштирилганлигини ва унинг полимеризацийини кучайтиришини аниқлади. Натижада имплантни ўраб турган тирик тўқималарга кремний катионларининг тарқалиши камаяди ва натижада материалнинг биоактивлиги пасаяди. Кремний катионларининг тарқалиши биоактив шиша ва тананинг суж тўқималари ўртасида юзага келадиган кимёвий реакцияларнинг ажралмас қисми бўлганлиги сабабли, B<sub>2</sub>O<sub>3</sub> нинг тананинг тирик тўқималарига билвосита токсик таъсири ҳақида хам гапиришимиз мумкин. Бу сужнинг нормал физиологик тикланишини камайишига ва суж нуқсонининг бўш жойини тўлдиришга мойил бўлган биритиравчи тўқималарни қўпайтиришда ўзини намоён қиласи.

Истисно ҳолатларида, B<sub>2</sub>O<sub>3</sub> мавжуд бўлганда аморф калций фосфатлар ҳали ҳам био-шиша юзасига қўйилганда, уларнинг кейинги минерализацияси содир бўлмайди, бу еса ўз навбатида имплантни рад етишга олиб келиши мумкин.

Шундай қилиб, B<sub>2</sub>O<sub>3</sub> ни БГ-1Д таркибидан чиқариш биоактив шишанинг остеоиндуктив хусусиятларини яхшилади.

### **Список литературы:**

1. Akbarov A. N., Ziyadullaeva N. S., Khabilov B. N. The using of osteoplastic materials for restoration of cavity defects of the maxillofacial bones //Stomatologiya. Tashkent. – 2019. – №. 2. – С. 67-72.
2. Ziyodullaeva N. Modern ideas about the use of scaffolds (literature review) //KRS Journal of Medicine. – 2021. – Т. 1. – №. 1. – С. 22-29.
3. Tulyaganov D. U. et al. In Vivo Evaluation of 3D-Printed Silica-Based Bioactive Glass Scaffolds for Bone Regeneration //Journal of Functional Biomaterials. – 2022. – Т. 13. – №. 2. – С. 74.